



## High Performance Water-soluble Mold Release Agent

# “Resiner NSW-B”

“Resiner NSW-B” is a revolutionary water-soluble mold release agent.

Its performance destroys stereotype for water-base agents.

You will realize a number of advantages once you try “Resiner NSW-B”.

### **Mainly used for :**

All of vibrational compaction products

### **Features :**

1. White-oriented finish compared with oil-based mold release agent
2. High release power in spite of water-soluble type
3. Less air bubbles and beautiful surface
4. Remarkable cost-effectiveness because of high dilution ratio “NSW : Water = 1:2 to 1:6”
5. Our one of most popular water-soluble concrete mold release agents
6. Many of our customers who used to prefer oil-base agents have changed to NSW series.

### **Main component & Property :**

1. Mineral oil, Special additives, Surfactant agent as main ingredients
2. Undiluted solution is oily liquid.

### **How to Use :**

1. Dilute by adding 2 to 6 parts of water to 1 part of “Resiner NSW-B”, and stir adequately.
  - The dilution ratio may need to be changed depending on your conditions especially vibration.
2. Apply the diluted “Resiner NSW-B” to a mold with spray or soft cloth/brush or sponge.
3. A good timing of casting fresh concrete is when the emulsion white has turned transparent, in other words water has dried up.
  - “NSW-B” can exert its performance by water’s drying up after the application.
4. If a mold is exposed to direct sunshine for more than 1 day subsequent to the application, which may cause negative influences on a product such as stains etc.
5. Please dilute only One(1) day portion every single day because the diluted liquid is supposed to be separated afterwards.

### **Remarks :**

1. Please refrain from storage under direct sunshine.
2. Be careful about rainwater intrusion.

### **Size Variations :**

1. 200L Drum
2. 18L Square Can

\* Sample is available. \*Please ask the person in charge below for details.

**\* Contact Information**

**SHIN-ETSU Industry Co., Ltd.**

**Mr. Takafumi Nagasaka/Sales Division**

**Email [nagasaka@shin-etsu.co.jp](mailto:nagasaka@shin-etsu.co.jp)**

**Phone +81-48-812-1160**

**Mobile +81-80-2241-9401**

**Address 1-52-10, Akabane, Kita-ku, TOKYO**

**115-0045, JAPAN**

